

PLEXIGLAS® Reflections

Clear and colored

Product

PLEXIGLAS® Reflections are extruded polymethyl metacrylate (PMMA) sheets, with a one-side reflective mirror surface coating. An opaque back paint protects the coating.

PLEXIGLAS® Reflections are either classic silver or colored. In addition to smooth and high-gloss surfaces, several metallic satin and textured grades are available which are resistant to finger prints and scratches.

Properties

Besides the general properties of PLEXIGLAS® like

- Easy to fabricate
- High surface hardness
- Light weight – half the weight of glass
- 11 times more impact resistant than glass

PLEXIGLAS® Reflections possesses the following property:

- Highest brilliance and clarity comparable to glass mirrors (due to the high transmission of PMMA)

Applications

Applications for PLEXIGLAS® Reflections are as wide as its product range:

- Elegant retail displays and exhibitions
- P-O-P displays, especially perfume, cosmetics, jewelry and other high value products
- Attractive interior designs in hotels, lobbies, etc.
- Mirrors in cars, RV's, boats and planes

- Mirrors in schools, hospitals, hotels and other public areas
- Corner dome mirrors for intersecting pathways, in warehouses, factories or department stores

PLEXIGLAS® Reflections is intended for indoor use, but not in bathrooms, indoor swimming pools or saunas. It has only limited resistance to humidity and outdoor exposure. Outdoor use can be improved by covering the coated side with a clear PLEXIGLAS® sheet and carefully sealing the edges.

PLEXIGLAS® Reflections sheets are normally flammable with a B2 rating to DIN 4102.

Processing

PLEXIGLAS® Reflections can be machined with the same parameters and equipment as standard acrylic sheet. However, in some instances better results can be obtained if the orientation of the decorative surface is taken into account during fabrication. Make sure the cutting tools used for sawing, drilling, routing and edge treatment enter the coated surface and exit through the uncoated surface.

Bonding. When bonding PLEXIGLAS® Reflections on the non-coated side, the same methods and adhesives commonly used for PLEXIGLAS® can be applied. If bonding the coated surface, the adhesives may attack and destroy the reflective coating.

To avoid delamination, the coated side of PLEXIGLAS® Reflections mirror should be treated with the same care as any other mirror. This means tapes, films, foams and adhesives used for fastening must be compatible with the protective lacquer.

Installation:

Because of its elasticity, PLEXIGLAS® Reflections readily adapts to any unevenness. The substrate is the first condition for obtaining a good optical appearance with PLEXIGLAS® Reflections. Correct fastening also plays a crucial role.

PLEXIGLAS® Reflections can be fastened for example on all sides in clamping profile systems, by **linear fastening in a clamping system** along the top edge, by double-sided **adhesive** foam tapes **applied as strips**, or by double-sided adhesive films or foams **across the entire surface of the material**.

The use of adhesive tapes to fasten PLEXIGLAS® MIRROR XT may lead to slight optical distortions depending on the product used. These are not obtrusive when viewed close up, however.

Bonding across the entire surface is recommended especially for large mirrors where a good optical effect (low distortion) is important. It should be borne in mind that the intermediate layer of the surfaces to be bonded must allow for **differences in expansion due to heat and humidity**.

Bonding should be performed on a clean, flat surface. Paint runs, pimples and similar irregularities should be sanded down and the resulting dust wiped off with a damp cloth.

Forming. PLEXIGLAS® Reflections can be cold-curved in two dimensions. The following minimum bending radii are to be observed: 330mm x sheet thickness in mm.

Spherical forming of PLEXIGLAS® Reflections is only conditionally possible by installation under constraint (cold forming).

Line-Bending and thermoforming. Hot line bending and thermoforming of PLEXIGLAS® Reflections mirror is not recommended since the mirror surface may become dull and the protective coating at the back may chip off.

Storage. Store PLEXIGLAS® Reflections horizontally on a perfectly flat surface. Sheets should not be stored vertically, or stored near heat sources.

Cleaning. Clean PLEXIGLAS® Reflections with a mild soap solution or cleaning agent and lukewarm water. Use a soft, clean cloth applying only light pressure (no rubbing).

Product range

PLEXIGLAS® Reflections is available in the following grades and sizes:

PLEXIGLAS® Reflections

Color and grade	Thickness	Size
Clear 0Z025	2–5mm	3050mmx2050mm
Clear 0Z025	6–20mm	on request

Upon request numerous colors and satin surfaces are available. For details please refer to the Sales Handbook.

Technical data

For typical test data of PLEXIGLAS® Reflections please see the Technical Information PLEXIGLAS® GS/XT (211–1).

® = registered trademark PLEXIGLAS is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany. Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

Evonik Industries is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Industries AG

Acrylic Polymers

Kirschenallee, 64293 Darmstadt, Germany

info@plexiglas.net www.plexiglas.net www.evonik.com

Ref. No. 232–26 August 2013